


ZIBELINE INTERNATIONAL™
P U B L I S H I N G

ISSN: 2222-7059 (Print)

EISSN: 2222-7067 (Online)

Advances in Industrial Engineering and Management (AIEM)

DOI: <http://doi.org/10.7508/aiem.01.2025.11.14>

RESEARCH ARTICLE

RECENT PROGRESS AND OBSTACLES IN PEROVSKITE SOLAR CELL TECHNOLOGY: ADVANCEMENTS IN MATERIAL SCIENCE AND DEVICE ENGINEERING

Yun Li

China General Nuclear New Energy Investment (Shenzhen) Co., Ltd. Tibet Branch, Lhasa 859000, China
Corresponding Author E-mail: l203304y@163.com

This is an open access article distributed under the Creative Commons Attribution License CC BY 4.0, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

ARTICLE DETAILS

Article History:

Received 12 February 2025

Revised 17 March 2025

Accepted 19 March 2025

Available online 21 March 2025

ABSTRACT

Perovskite-based solar cells have emerged as a promising technology due to their exceptional efficiency and cost-effective production potential. This paper provides an overview of the recent breakthroughs in improving the efficiency and long-term stability of perovskite materials. It delves into strategies for enhancing the structural design and performance of various perovskite compositions, with a focus on the development of tandem and multi-junction solar cell architectures. Additionally, the paper examines advanced manufacturing processes, including solution-based techniques and roll-to-roll production. The influence of electron transport and buffer layers on overall cell performance is discussed, as well as the implementation of passivation methods to improve material stability. In conclusion, the challenges and opportunities for scaling up perovskite solar cells for commercial use are analyzed, providing insights into future directions for this rapidly advancing field.

KEYWORDS

Perovskite, Photoelectric Conversion Efficiency, Structural Optimization, Manufacturing Techniques, Stability

1. INTRODUCTION

In the face of global climate change and the pressing energy crisis, there has been a growing consensus worldwide on the need to develop sustainable and renewable energy sources (Hwang et al., 2015). Among the various solutions, solar energy, specifically through photovoltaic technology, stands out as one of the most promising options for future energy production (Kim et al., 2015). Although silicon-based solar cells have seen significant progress in efficiency and cost reduction over the years, their continued improvement faces inherent technical limitations (Koh et al., 2014). Moreover, the complexity of their manufacturing process and the need for high-temperature treatments result in relatively high production costs. As a result, perovskite solar cells (PSCs) have emerged as an exciting alternative in the photovoltaic sector, owing to their remarkable material properties, lower production costs, and simpler fabrication methods. First introduced in 2009 with an efficiency of just 3.5% (Li et al., 2015), PSCs have experienced rapid advancements, with their efficiency now exceeding 25%, approaching that of conventional silicon solar cells (Barrows et al., 2014). This swift development has attracted significant interest from both the scientific community and the industry, with perovskite materials being heralded as a major breakthrough in next-generation solar technologies.

The unique characteristics of perovskite materials contribute to their suitability for solar energy applications. One of the most notable features is their tunable bandgap, which can range from 1.1 to 2.3 eV, allowing them to efficiently absorb a broad range of solar spectrum photons, thereby enhancing the photoelectric conversion efficiency (Han et al., 2015). Additionally, perovskite materials typically exhibit a high absorption coefficient, meaning they can effectively capture light even when used in thin layers, reducing both material consumption and associated costs (Berhe et al., 2016). The superior charge carrier mobility and extended diffusion lengths of perovskites further improve performance by facilitating the rapid movement of photogenerated charge carriers, minimizing recombination losses, and improving device efficiency (Tan et al., 2014). In addition to these performance advantages, perovskite solar cells benefit from relatively simple and low-cost manufacturing processes. Techniques such as solution spin-coating and vacuum deposition are easy to implement and can be carried out at low temperatures, significantly reducing both manufacturing costs and energy usage (Zhu et al., 2014). This makes perovskite solar cells a highly attractive option for large-scale commercialization in the solar energy market.

Despite the significant progress made in enhancing the efficiency and reducing the cost of perovskite solar cells, several challenges remain

Quick Response Code



Access this article online

Website
www.aiem.com.my

DOI:
[10.7508/aiem.01.2025.11.14](https://doi.org/10.7508/aiem.01.2025.11.14)

in their path to full-scale commercial deployment. The most significant of these is the stability of the perovskite materials, which are highly susceptible to degradation when exposed to environmental factors such as moisture, oxygen, and temperature fluctuations (Pazos-Outón et al., 2016). Addressing this instability is crucial for the long-term reliability of perovskite solar cells. Furthermore, although laboratory techniques like spin-coating have enabled the production of high-efficiency PSCs, they are not suitable for mass production. Thus, transitioning from small-scale laboratory methods to large-scale industrial processes, such as roll-to-roll manufacturing, is a key hurdle for commercialization. Another important avenue of research is the development of lead-free, environmentally friendly perovskite materials and the exploration of multi-junction solar cells, both of which have the potential to further enhance efficiency and reduce the environmental impact of perovskite-based technology. This review aims to provide a detailed overview of the evolution of perovskite solar cells, examining the effects of different material structures and fabrication methods on their performance, while addressing the challenges related to stability and scaling up production. Finally, the paper will discuss potential future directions for research and the commercialization prospects of perovskite solar cells, offering valuable insights for the continued advancement of this exciting technology.

2. PEROVSKITE MATERIAL STRUCTURE AND FABRICATION APPROACHES

The exceptional efficiency of perovskite solar cells is largely due to the unique structural properties of their constituent materials, coupled with their superior optoelectronic characteristics. Perovskite compounds generally follow the formula ABX_3 , where "A" represents either an organic or inorganic cation (such as methylammonium, $CH_3NH_3^+$, or cesium, Cs^+), "B" is a metal cation (commonly lead, Pb^{2+} , or tin, Sn^{2+}), and "X" is a halide anion (such as iodine, I^- , bromine, Br^- , or chlorine, Cl^-). This arrangement enables the material to possess a tunable bandgap, a broad range of light absorption, and efficient charge carrier transport properties (Park et al., 2015).

As shown in Figure 1, the core component of a perovskite solar cell is the light-absorbing perovskite layer. When sunlight strikes this layer, the photon energy excites electrons from the valence band to the conduction band, resulting in the creation of electron-hole pairs. These excited charge carriers are then driven towards the respective electron transport layer (ETL) and hole transport layer (HTL), facilitated by the internal electric field within the device (Meloni et al., 2016).

In Figure 1, the perovskite layer is positioned between two transport layers: the electron transport layer (typically composed of TiO_2 or ZnO) and the hole transport layer (such as PEDOT or Spiro-OMeTAD). The electron transport layer's function is to transfer the photogenerated electrons from the perovskite layer to the top electrode, while simultaneously blocking holes to prevent recombination. Conversely, the hole transport layer directs the generated holes toward the bottom electrode and prevents electron migration in the opposite direction. This strategic arrangement of transport layers ensures efficient charge separation and migration, which contributes significantly to the overall improvement in photoelectric conversion efficiency (Ke et al., 2015). In addition to their strong absorption properties, perovskite materials possess long carrier diffusion lengths, which help reduce recombination losses as the charge carriers move towards the electrodes. These features make perovskite materials an ideal choice for fabricating high-efficiency solar cells, owing to their unique crystalline structure and superior optical performance (Hanusch et al., 2014).

The synthesis method of perovskite solar cell materials directly affects their performance. Traditional high-temperature synthesis methods, while capable of producing highly crystalline perovskite films, are limited by their complex processes and high energy consumption, which restricts their potential for large-scale application. To overcome these limitations, low-temperature synthesis techniques have been widely researched and applied in recent years, which not only reduce production costs but also enhance the material's applicability, especially in flexible electronic devices.

Among the low-temperature synthesis methods, spin-coating and solution processing technology are the most commonly used. Spin-coating (shown in Figure 2a) is a technique that spreads the perovskite precursor solution uniformly across the substrate by utilizing centrifugal force. After the solution undergoes low-temperature annealing, a smooth and compact perovskite film is created. This method is straightforward and easy to execute, making it ideal for early-stage research in laboratories and small-scale manufacturing applications. However, for large-scale production, solution processing technology (Figure 2b) shows greater potential. This technology dissolves the precursor in an appropriate solvent, and then undergoes annealing at low temperatures to form a uniform perovskite film. This technique is suitable for continuous large-area production and is compatible with flexible substrate materials.

As an advanced extension of solution-based fabrication, roll-to-roll




Figure 1: Schematic of a Perovskite Solar Cell Architecture




Figure 2: Perovskite Solar Cell Fabrication Methods: (a) Spin-Coating Method; (b) Solution Processing Method

processing has emerged as a key technique for driving the large-scale production of perovskite solar cells. This method enables continuous, high-speed manufacturing at a lower cost, making it particularly advantageous for producing extensive photovoltaic modules. By significantly enhancing production efficiency and reducing expenses, roll-to-roll technology is poised to accelerate the widespread adoption and commercialization of perovskite solar cells.

3. EFFECT OF ADVANCED INTERFACE AND ELECTRODE MATERIALS ON SOLAR CELL PERFORMANCE

In the development of perovskite solar cells, it is crucial to optimize not only the perovskite light-absorbing layer but also the materials used for the electron transport layer (ETL) and hole transport layer (HTL), as these layers greatly influence the overall efficiency of the device. As depicted in Figure 1, the perovskite layer is positioned between two transport layers, facilitating the effective separation and migration of charge carriers. This design reduces the chances of recombination and contributes to higher photoelectric conversion efficiency. The electron transport layer often employs semiconductor materials like titanium oxide (TiO_2) or zinc oxide (ZnO), which selectively conduct electrons while blocking hole movement, thereby minimizing recombination losses. Conversely, materials like Spiro-OMeTAD (an organic small molecule) and PEDOT (a conductive polymer) are commonly used in the hole transport layer to efficiently guide holes to the bottom electrode, while preventing the reverse migration of electrons.

The choice of electrode materials is another critical factor in determining the performance of perovskite solar cells. Although traditional electrodes such as gold (Au), silver (Ag), and aluminum (Al) offer excellent conductivity, their high cost and potential for chemical reactivity present challenges for large-scale manufacturing (McGehee, 2014). Carbon-based materials have recently emerged as a viable alternative, offering low cost, excellent conductivity, and stability, which makes them an attractive option for scaling up production. By optimizing both the interface and electrode materials, perovskite solar cells have achieved notable improvements in efficiency and long-term stability. Despite these advancements, the sensitivity of perovskite materials to environmental conditions, especially moisture and oxygen, remains a significant hurdle. These elements can cause rapid degradation of the perovskite layer, leading to a decline in the device's performance and lifespan. Overcoming this issue is essential for the widespread commercialization of perovskite solar cells.

Material Modification: By introducing more stable inorganic cations (such as cesium ions Cs^+) or employing mixed cation strategies, the moisture and thermal stability of perovskite materials can be enhanced. For example, studies have shown that partially replacing organic cations (such as methylammonium CH_3NH_3^+) with inorganic cations can significantly improve the material's moisture resistance and thermal stability. Additionally, the incorporation of halide anions such as fluoride (F^-) can also enhance the degradation resistance of perovskite materials to some extent.

(2) Encapsulation Technology: Effective encapsulation technology is crucial for improving the environmental stability of perovskite solar cells. Currently, researchers are developing multi-layer encapsulation structures, including the use of polymer waterproof layers, metal oxide protective layers, and encapsulation films with low water vapor transmission rates. These encapsulation strategies can significantly slow the penetration of moisture and oxygen, protecting perovskite materials from environmental impacts, thereby extending the device's lifespan.

(3) Interface Engineering Optimizing the materials and structures at the interface can significantly reduce defects and instabilities. Effective interface engineering enhances both the efficiency of charge carrier separation and the overall stability of the device over time. For instance, the application of self-assembled monolayers (SAMs) or passivation agents at the interface helps to minimize defects and improve the material's durability.

4. CONCLUSION

The remarkable properties of perovskite materials, alongside the advancements in low-temperature fabrication techniques and the optimization of interface and electrode materials, are critical factors that enhance the performance of perovskite solar cells. These developments not only accelerate the progress of perovskite-based solar technologies but also open up possibilities for large-scale commercialization. As these innovations continue to mature, perovskite solar cells are expected to play a central role in the future of solar energy applications.

REFERENCES

- Barrows, A. T., Pearson, A. J., Kwak, C. K., et al. (2014). Efficient planar heterojunction mixed-halide perovskite solar cells deposited via spray-deposition. *Energy & Environmental Science*, 7(9), 2944-2950. <https://doi.org/10.1039/C4EE01546K>

- Berhe, T. A., Su, W. N., Chen, C. H., et al. (2016). Organometal halide perovskite solar cells: degradation and stability. *Energy & Environmental Science*, 9(2), 323-356. <https://doi.org/10.1039/C5EE02733K>
- Han, Y., Meyer, S., Dkhissi, Y., et al. (2015). Degradation observations of encapsulated planar CH₃NH₃PbI₃ perovskite solar cells at high temperatures and humidity. *Journal of Materials Chemistry A*, 3(15), 8139-8147. <https://doi.org/10.1039/C5TA00358J>
- Hanusch, F. C., Wiesenmayer, E., Mankel, E., et al. (2014). Efficient planar heterojunction perovskite solar cells based on formamidinium lead bromide. *The Journal of Physical Chemistry Letters*, 5(16), 2791-2795. <https://doi.org/10.1021/jz501237m>
- Hwang, K., Jung, Y. S., Heo, Y. J., et al. (2015). Toward large scale roll-to-roll production of fully printed perovskite solar cells. *Advanced Materials*, 27(7), 1241-1247. <https://doi.org/10.1002/adma.201404598>
- Ke, W., Fang, G., Liu, Q., et al. (2015). Low-temperature solution-processed tin oxide as an alternative electron transporting layer for efficient perovskite solar cells. *Journal of the American Chemical Society*, 137(21), 6730-6733. <https://doi.org/10.1021/jacs.5b01994>
- Kim, J. H., Liang, P. W., Williams, S. T., et al. (2015). High-performance and environmentally stable planar heterojunction perovskite solar cells based on a solution-processed copper-doped nickel oxide hole-transporting layer. *Advanced Materials*, 27(4), 695-701. <https://doi.org/10.1002/adma.201404189>
- Koh, T. M., Fu, K., Fang, Y., et al. (2014). Formamidinium-containing metal-halide: an alternative material for near-IR absorption perovskite solar cells. *The Journal of Physical Chemistry C*, 118(30), 16458-16462. <https://doi.org/10.1021/jp411112k>
- Li, X., Ibrahim Dar, M., Yi, C., et al. (2015). Improved performance and stability of perovskite solar cells by crystal crosslinking with alkylphosphonic acid ω -ammonium chlorides. *Nature Chemistry*, 7(9), 703-711. <https://doi.org/10.1038/NCHEM.2324>
- McGehee, M. D. (2014). Perovskite solar cells: Continuing to soar. *Nature Materials*, 13(9), 845-846. <https://doi.org/10.1038/nmat4050>
- Meloni, S., Moehl, T., Tress, W., et al. (2016). Ionic polarization-induced current-voltage hysteresis in CH₃NH₃PbX₃ perovskite solar cells. *Nature Communications*, 7(1), 10334. <https://doi.org/10.1038/ncomms10334>
- Park, J. H., Seo, J., Park, S., et al. (2015). Efficient CH₃NH₃PbI₃ perovskite solar cells employing nanostructured p-type NiO electrode formed by a pulsed laser deposition. *Advanced Materials*, 27(27), 4013-4019. <https://doi.org/10.1002/adma.201500523>
- Pazos-Outón, L. M., Szumilo, M., Lamboll, R., et al. (2016). Photon recycling in lead iodide perovskite solar cells. *Science*, 351(6280), 1430-1433. <https://doi.org/10.1126/science.aaf1168>
- Tan, K. W., Moore, D. T., Saliba, M., et al. (2014). Thermally induced structural evolution and performance of mesoporous block copolymer-directed alumina perovskite solar cells. *ACS Nano*, 8(5), 4730-4739. <https://doi.org/10.1021/nn500526t>
- Zhu, Z., Ma, J., Wang, Z., et al. (2014). Efficiency enhancement of perovskite solar cells through fast electron extraction: the role of graphene quantum dots. *Journal of the American Chemical Society*, 136(10), 3760-3763. <https://doi.org/10.1021/ja4132246>

